



# ESD Basecoat 2020

## 1 PRODUCT DESCRIPTION

Special highly conductive waterbased 2 part polyurethane sealer. For the long-term protection of conductive PVC and epoxy resin floorings.

- With high horizontal and vertical conductivity for the renovation of conductive floorings prior to finishing with **Dr. Schutz ESD Topcoat**.
- Fulfills the requirements of EN 61340-5-1, ANSI/ESD S20.20 (IEC 61340-4-1,4-5, ANSI S7.1, ESD STM97.1) as well as the requirements for explosion prevention areas according to TRBS 2153.
- Hardwearing sealer film, excellent elasticity and good resistance against colorless chemicals.
- Only for professional users.
  
- Easy and safe to apply with excellent adhesion.
- High solids content.
- No intrinsic yellowing.

Certified by GOD-MIN Mernoki Kft.- GOD-MIN Laboratory, Hungary

## 2 SUITABLE FOR

Conductive PVC and Epoxy Resin floorings with a plain structured surface.

## 3 APPLICATION

Stir up well. Completely add set portion of **Crosslinker M** to the base lacquer and immediately mix thoroughly and evenly. Allow the mixture to settle for 10 minutes, then stir again and use it. Do not mix more than can be used up within 2 hours (at 20 °C). Apply **ESD Basecoat** evenly in two layers (at min. 15 °C) onto the previously professionally prepared subsurface (Please pay attention to our Technical Information „Preparation of subsurfaces“) with the **Dr. Schutz Aquatop Roller**.

Please note:

- The surface must be professionally prepared and abraded as well as in a clean and dry condition, free of oil, wax and dust.
- Mixing ratio: 5 kg base lacquer to 0,5 l Crosslinker.
- Start rolling out only with full saturated rollers. We recommend for this usage of a separate roller tray.
- Slightly visible roller marks can be caused by detrimental environmental conditions like humidity, temperature and floor color but this does not affect the conductivity properties of the system.
- Floor and material temperature must not fall below +15°C during application and drying time.
- The technical rules are to be observed.

## 4 COVERAGE

Per coating approx. 50 ml/m<sup>2</sup> (20 m<sup>2</sup>/l).



## ESD Basecoat 2020

### 5 CURING

Can be carefully walked on and worked on for the subsequent coating after approx. 2 hours, but no longer than 12 hours after the first coat. In the case of a longer drying time the entire surface must be intermediate sanded.

Low temperatures, high humidity and poor ventilation can prolong the drying time. Refrain from laying down carpets in the first 10-14 days. Furniture can be carefully placed. The area must not be wet mopped in the first three days.

### 6 MAINTENANCE

see Dr. Schutz ESD Topcoat

### 7 STORAGE

Protect against frost. Store in a cool, dry place. Will keep for 12 months in unopened, original canister from the date of manufacture. Keep coating materials out of the reach of children.

When stored in varying temperatures and/or in an opened canister, dried parts can form. If so, sieve these out before using.

### 8 TECHNICAL DATA

Contained substances: water, polyacrylate, polyurethane, glycoether, silicic acids, waxes, additives. Contains 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction.

voc (g/l) 73 in mixture (ISO11890) / GISCODE: W3DD+ / Decopaint 2004/42/IIA(j)(140)140.

ADR/RID: not a dangerous good as defined by transport regulations (base lacquer and crosslinker).

CLP (base lacquer): not obliged for labelling. For safe handling take care of the actual Safety Data Sheet.

CLP (Crosslinker M): obliged for labeling. For safe handling take care of the actual Safety Data Sheet.

Emptied canisters can be disposed of in household waste or taken to a recycling centre.

### 9 SPECIAL NOTES

- When mixed together, 2part-products can develop carbon dioxide and build up pressure. Never close 2part-mixtures tightly in a container, danger of bursting!
- We recommend to ascertain the conductivity installation of a sample area.
- Please pay attention to the printed batch number. Only use products with the same batch number in one layer. In the case of a different batch, mix this in a separate container before using.
- All details given under laboratory conditions 23°C / 50% relative humidity / air-change 3 times per hour. Conditions at building sites can differ and account for varying results.



## ESD Basecoat 2020

- Due to greyish shade resulting from the conductive filler we recommend sampling for release by customer prior to work.
- Clean the working tools and implements with water. The hardened remains of lacquer can only be removed mechanically. We recommend always using new, dry Aquatop Rollers.
- Please pay attention to the printed batch number. Only use products with the same batch number in one layer. In the case of a different batch, mix this in a separate container before using.
- Colored products (e.g. hair dyes, colored disinfectants for wounds) as well as plasticizer migration (e.g. from rubber) can lead to the irreversible discoloration of the sealing coat. If resistance to hand and instrument disinfectants is required in specific buildings, we recommend pre-testing the respective chemicals on site.

### 10 CROSS-REFERENCE

Our following publications in their updated form are valid as an integral part of this fact sheet:

- General notes on the application of Dr. Schutz finishes
- Safety data sheet available on request.

The quoted printed matter, as well as this product information in its updated form, is available on our homepage [www.dr-schutz.com](http://www.dr-schutz.com) or on request from the address quoted below.

### Dr. Schutz – We Care About Floors

Headquarter  
Dr. Schutz GmbH  
Holbeinstraße 17  
D-53175 Bonn  
Tel.: +49 (0)228 / 95 35 2-40  
Fax: +49 (0)228 / 95 35 2-46  
E-Mail: [export@dr-schutz.com](mailto:export@dr-schutz.com)  
[www.dr-schutz.com](http://www.dr-schutz.com)

UK  
Dr. Schutz U.K Ltd.  
Unit 24, Anglo Business Park,  
Smeaton Close, Aylesbury Bucks  
HP19 8UP

Contact: Richard Nelson  
Tel.: 0044 / 1296 437827  
Fax: 0044 / 1296 334219  
E-Mail: [richard@dr-schutz.com](mailto:richard@dr-schutz.com)

Ireland  
Dr. Schutz Ireland  
35 Pic Du Jer Park,  
Ballinlough, Cork

Contact: Paul O'Reardon  
Mobile: 0877678388  
E-Mail: [drschutzireland@gmail.com](mailto:drschutzireland@gmail.com)

North America  
Schutz NA  
4701 Bath St 46  
Philadelphia PA 19137  
USA

Contact: Sam Jamison  
Tel.: +1 (877) 272-4889  
Mobile: +1 (215) 510-7874  
E-Mail: [sam@schutzNA.com](mailto:sam@schutzNA.com)

The above advice for technical application is given to the best of our knowledge and according to the latest state of technology. Therefore, if our products are used carefully heeding the advice given on their application, as well as following our suggested procedures with the materials intended for use with these products, no damage shall occur. However, our products are used outside and beyond our possible control, and are therefore subject to your own responsibility, which does not release you from the obligation to check for yourself whether our supplied products are suitable for your intended purpose and procedure. Therefore our notes and advice are not legally binding and cannot be used against us as grounds for liability - which includes the rights and protection of any third party. The relevant recommendations, guidelines and standard norms are to be observed, as well as the recognized technical rules. On publication, this product information replaces and supersedes the validity of any previous versions.